




## Packaging

- The leading supplier for the world's largest manufacturers of packaging products
- Years of expertise in production of the most demanding semi-products in terms of mechnical properties
- Full value chain from casting to slitting recycling in all manufacturing sites







Gränges Konin semi-finished products are used in the following industries and applications:

- closures
- foilstock
- tea-lights

- grill trays
- aluminium containers
- cans for fish and seafood products
- beverage cans lids
- lipstick containers
- bulk material containers













Most commonly used alloys							
8xxx	1xxx	Зххх	5801				
	Thickness mm	Width mm	Length mm				
	0.06÷0.40*	12÷1500**					
STRIPS - COLD ROLLED	0.40÷2.00	20÷1500**					
	2.01÷4.00 (5.00)***	30÷1500**					
"* For strips in alloys 1xxx series thickness range is 0.12÷0.40 and 0.20÷0.40 for strips in alloys 5xxx/4xxx series							

<sup>\*\*</sup> The width depends to the tcikness, above width 1500mm after previous agreement of technical requirements
\*\*\* Thickness 4-5mm depends to the width, alloy, temper

	Thickness mm	Width mm	Length mm				
	Alloys 8xxx series						
	0.20÷0.50* 750÷1500		500÷2500				
	Alloys 1xxx, 5xxx and 3xxx series						
	0.20÷0.40	500÷2500					
	0.40÷2.00 800÷1500		1000÷6000				
SHEETS - COLD ROLLED	2.00÷3.00	900÷1500	1000-0000				
	3,00÷4,00 (5,0)**	1000÷1500	1400÷6000				
	Patterned sheets - FIVE BAR (EN AW - 1050A)						
	2.00÷4.50	1400÷6000					
	Patterned sheets - STUCCO (EN AW - 1050A)						
	0.40÷1.20	1000÷1500	1000÷6000				

<sup>\*\*</sup> It's possible to produce other range of dimensions after previous agreement of technical requirements between customer and manufacturer
\*\* Thickness 4-5mm depends to the width, alloy, temper

# Innovative 5801 alloy

5801 is a new aluminium alloy developed by Gränges Konin, dedicated for high pressure bottle closures. New chemical composition and properly designed technology of production allow the pressing of high caps resistant to high pressure.

The alloys are characterized by higher mechanical properties than other alloys, which are used for bottle caps like EN AW-8011A. Excellent adhesion of a varnish and high thermal resistance make this material perfectly suitable for the lacquering processes. For maximal reducing of scrap rate during deep drawing process, 5801 aluminium alloys sheets show very low earing, caused by planar



#### Dedicated for:

- high pressure bottles
- deepdrawing bottle caps
- easier opening of the bottle
- high-quality, fragile material
- easier opening or the bottle

#### Infinitely recycable:

- based on recycled material
- finished product 100% recyclable

#### Enhanced material resistance to:

- mechanical damage
- temperature



#### CHEMICAL COMPOSITION 5801/8011A /3105

Alloy		Si Fe	E <sub>a</sub>	0	.,		Mg Cr	Zn	Ti	V	others	
			re	Cu	Mn	Mg					each	total
5801	min	0,75	0,1	0,05	0,25	0,8	-	-	0,010	0,03	-	-
5601	max	1,10	0,4	0,35	0,65	1,2	-	0,15	0,15	0,2	0,05	0,15
00114	min	0.40	0.50	-	-	-	-	-	-	-	-	-
8011A	max	0.8	1.0	0.10	0.10	0.10	0.10	0.10	0,10	0.05	0,05	0,15
3105A	min	-	-	-	0,30	0,20	-	-	-	-	-	-
	max	0,6	0,7	0,30	0,8	0,8	0,20	0,25	0,10	-	0,05	0,15

#### MECHANICAL PROPERTIES

Alloy	Temper	R <sub>m</sub> [MPa]	R <sub>p02</sub> [MPa]	A <sub>50</sub> [%]
5801	H14	125-160	min. 100	min. 3
8011A	H14	110-150	90-130	min. 3
7405 4	H16	170-210	150-190	min. 1
3105A -	H24	150-190	120-160	min. 3

Gränges Konin S.A. certifies the mechanical properties for material in delivery condition.

#### SURFACE PRETREATMENT 5801/8011A/3105A

Degreased, leveled, phosphate-titanium conversion layer and oiled (DOS).

Layer weight of DOS coating: 3-6 mg/m² per side (recommended 4,5 mg/m² per side).

#### **DIMENSIONS**

Product	Thickness [mm]	Width [mm]	Length [mm]	Squareness
5801	$0.18 - 0.30 \pm 0.010$ (it depends on final thickness)	700,0 - 1250,0 +0,6 / -0,0	500,0 - 1100,0 +1,0 / - 0,0	t ≤ 0,08% of sheet length
8011A	$0.18 - 0.30 \pm 0.010$ (it depends on final thickness)	700,0 - 1250,0 +0,6 / -0,0	500,0 - 1100,0 +1,0 / - 0,0	t ≤ 0,08% of sheet length
3105A	$0.18 - 0.30 \pm 0.010$ (it depends on final thickness)	700,0 - 1250,0 +0,6 / -0,0	500,0 - 1100,0 +1,0 / - 0,0	t ≤ 0,08% of sheet length

Changes are possible after mutual agreement.

### Your experienced partner

Built on the foundation of more than 125 years of innovative engineering and materials development, we are a world leader in high-performance aluminium alloys. With a long heritage of supplying the aluminium (semi-finished) materials to wide range of industries, we are an experienced partner delivering consistent, high quality materials to industries with high demands on safety, performance and sustainability.

#### → granges.com







### Contributing to a circular and sustainable economy Join us on the path to net-zero 2040

Gränges is a global leader in aluminium rolling and recycling in selected niches. We are committed to creating circular and sustainable aluminium solutions in partnership with our customers and suppliers – for a better future.

Our solutions help customers grow and transition to climate neutrality. They are used for efficient climate control in transportation and buildings, electrification and battery components, recyclable packaging, and more.

Malgorzata.Pilarska@granges.com